

JPL WEB TEAM

JET PROPULSION LABORATORY

D. B. Bickler

Web Team

- **Background**


- DOE Five-Year Research Plan goals significantly lowered the FSA \$/m² allowable for modules while raising efficiency requirements
- Silicon sheet costs have not kept pace with reductions in other areas of module fabrication
- Dendritic web viewed as most probable sheet option to meet both \$/m² and efficiency requirements
- Area throughput rate limiting factor for years in dendritic web economics

- | | |
|-------------------------------|--|
| • May 1983: | DOE issues Five-Year Research Plan |
| • June 1984: | JPL reviews ribbon situation and decides to broaden research base in dendritic web |
| • September 1984: | Web Team formed to take independent analytical and experimental look at web Purchase order placed with Westinghouse for fabrication and delivery of a web growth system |
| • November 1984: | JPL internal review of proposed Web Team activities |
| • December-January 1984-1985: | Two JPL operators trained at Westinghouse |
| • January 1985: | Facilities for growth system tested by exercising test bed furnace |
| • February 1985: | Growth system received at JPL |
| • April 1985: | Major external review of Web Team activities. First web grown at JPL |

PRECEDING PAGE BLANK NOT FILMED


ADVANCED SILICON SHEET

Computed Isotherms With and Without the Growing Web



Thermal modeling was done using the "SINDA" program to investigate the effect of varying key parameters


Crucible-to-Susceptor Gap Effect on Surface Temperature



Differential thermal expansion causes a varying gap between the crucible sides and the susceptor. Beyond 0.021 in., gap increase causes insignificant change in heat transfer


ADVANCED SILICON SHEET

Melt Surface Temperature Change as a Function of Lid Gap



Thermal warping of the molybdenum lids causes a change in heat transfer from the surface of the molten silicon. A 0.5 mm variation in lid gap may cause as much as 4°C change in melt surface temperature


Button Growth



The solid to liquid interface cannot be an isotherm (i.e., the freezing point). A simplified computer run gives a 5°C difference over actual button dimensions.


ADVANCED SILICON SHEET

Cold Shoe




A "cold shoe" design was analyzed for the feasibility of high heat transfer rates from the growing web. Analysis showed need for severe gradients in shoe as well as sensitivity to small dimensional changes. SiO contamination expected to be a major problem

Benard Cells



Vertical temperature gradients (from thermal analysis) indicate convection (Benard cells) in molten silicon causes instability at melt depths used

Meniscus Geometry




Meniscus shape is dictated by surface tension of the molten silicon. The meniscus is higher on the web where a cylindrical curvature exists. The end meniscus is pulled lower by the convex horizontal curvature component

Radio Frequency Studies

- **Objective**
 - **Devise means for determining radio frequency coupling with furnace elements**
- **Results**
 - **Mathematical methods are too complex, require simplifying assumptions which dominate results**
 - **Relatively simple probe, 25 turns 0.250 in. diameter with semi-rigid coaxial shaft**
 - **Without susceptor, inside field about twice that outside of coil**
 - **Susceptor with shields absorbs over 99.3% of the energy**
 - **No measurable field in vicinity of web**

ADVANCED SILICON SHEET

Scanning Thickness Detector



Sensing Head Optical System

Section 7 — MAINTENANCE & FIELD SERVICE

